

Underlay Technical Specification

Item Code: TAENERGY2

Issue Date: 02/07/2021

Issue No. 9

Sponge Rubber Textured Flat

Suitable for the stretch-fit installation of carpets

End Use Classification (BS 5808: 1991 / BS EN 14499 : 2015): GD/U, General Domestic Use

Standard Specifications*

Nominal thickness	7.00 mm (0.276")	ISO 1765
Nominal density	368kg/m ³ (22.97bs/ft ³)	
Nominal square weight	2576 g/m ² (76 oz/yd ²)	
Nominal roll weight	38.82 kg (86 lb)	
Nominal roll area	15.07m ² (1.33m x 11.33m); 18.02yd ² (53.94" x 433.07")	

BS 5808: 1991 / EN14499 : 2015

End Use Classification	GD/U, General Domestic Use	
Work of compression (Min. 50 J/m ² Max. 200 J/m ²)	118 J/m ²	BS 4098 & ISO 2094
Retention of work of compression (min 40%)	70 %	BS 4098 & ISO 2094
Compression after dynamic loading	4.1 mm	BS 4098 & ISO 2094
Loss in thickness after dynamic loading (max 15%)	4.8 %	BS 4052 & ISO 2094
Loss in thickness after static loading (max 15%)	9.3 %	ISO 3415/3416 & BS 4939
Resistance to cracking (not greater than 50mm)	Pass	EN 14499 & BS 5808


Test Performance to US Standards

CFD (Compression Force Deflection)	2.0 PSI @ 25% deflection.	ASTM D3676-13 Method: 601/12151
CFD (Compression Force Deflection)	4.5 PSI @ 50% deflection.	ASTM D3676-13 Method: 601/12151
CFD (Compression Force Deflection)	11.2 PSI @ 65% deflection.	ASTM D3676-13 Method: 601/12151

Recommended Use	Extra Heavy Traffic Class III	US Carpet Cushion Council GOST 12.1.044-89 (item 4.20)
-----------------	-------------------------------	--



Certification



Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.

Notes

* The nominal roll dimensions have been quoted. These may vary slightly but will comply with the requirements of BS EN 14499:2015

‡ Value derived from similar product test results

THIS PRODUCT IS PRODUCED IN A FACILITY ACCREDITED TO ISO 9001, 14001 & 45001

Underlay Technical Specification

Item Code: TAENERGY2

Issue Date: 02/07/2021

Issue No. 9



Flammability

Hot metal nut test	Low radius of effects of ignition	BS 4790 & BS 5287
US Methenamine Pill Test	Pass	Pill Test DOC-FF 1-70
US Smoke Chamber Test	Pass	ASTM E662
US Critical radiant flux NFPA	Class I	NFPA 253 / ASTM E648-03
Russian GOST FR Test	Classification KM5	GOST 30244-94, GOST 30402-96 GOST 51032-97, GOST 12.1.044-89 (item 4.18),


Other Specifications

Odour	No objectionable odour	
Antimicrobial and mildew resistant	Yes	
R value (SI Unit)	0.101	
R Value (USA Unit)	0.57	
Colour / backing	Red / printed Textron® backing	
Packaging	Grey film / red print	
Thermal resistance	1.01 togs	BS 4745
Impact sound reduction (Delta Lw)	30dB	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria Certified GLP051 Cat CC10 Ruber	US CRI Green Label Plus Programme

GREEN CREDENTIALS

Green Features	Description	LEED Programme
Recyclable	At the end of the underlays useful life it can be 100% recycled	MR 2.0: Points Available It can be recycled
Recycled Content	Contains not less than 3% pre-consumer recycled material	MR 4.0: Points Available Recycled Content
Indoor Air Quality	Meets or exceeds the industry standard for indoor air quality as established by the CRI Green Label Plus Programme	IEQ 4.3: Points Available Product is Green Plus Label Certified
Regional Materials	Production Facility Haslingden BB4 4LS, UK Where used within 500 miles of Production Facility	MR 5.0: Points Available

Certification



LEED points must be considered along with other building components and must be determined by the specifier/architect or LEED accredited professional

Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.

Notes

- * The nominal roll dimensions have been quoted. These may vary slightly but will comply with the requirements of BS EN 14499:2015
- ‡ Value derived from similar product test results

THIS PRODUCT IS PRODUCED IN A FACILITY ACCREDITED TO ISO 9001, 14001 & 45001